



Confederate Chemicals Ltd

Mochdre Industrial Estate Newtown Powys SY16 4LE

Emerg. tel: 01686 627158

w: www.confederatechemicals.com w: www.paintstrip.com



LEKTROSOAK –TECHNICAL DATA SHEET

Description

An off-white highly alkaline powder, for use as an electrolytic cleaner for steel prior to electroplating or vitreous enamelling. LEKTROSOAK can also be used by immersion but where added detergency is required LEKTROSOAK EXTRA may be preferable. This product contains surfactants considered by our suppliers to be >80% biodegradable when tested by the OECD screening test which satisfies EEC directives 82/242 and 82/243.

The Control of Substances Hazardous to Health Regulations 2002 (COSHH)

For a Safety Data Sheet on this product please contact Confederate Chemicals by telephone, or by e-mail at lab@confederatechemicals.co.uk

Instructions for use

	Electrolytic	Immersion
Concentration:	35 - 75 gm/litre	35 - 75 gm/litre
Temperature:	50 - 85°C	55 - 95°C
Time:	0.5 to 8 minutes	2 - 10 minutes
Current Density:	3 - 11 amp/dm ² Anodic or Cathodic	N/A

Control

Titrate a 10ml sample of the LEKTROSOAK bath against Normal Hydrochloric Acid to the methyl orange end point. Each ml of 1.0N HCl is equivalent to 5.3gm/litre LEKTROSOAK in solution.

Equipment

Mild steel plant and equipment are suitable. Aluminium is unsuitable. Non ferrous should be avoided.

Storage

Store in dry, remote from foodstuffs, in closed containers.

OCT 2016

\\Technical Data Sheets\Lektrosoak V2.doc